



PRODUCT GUIDE: LINERS

Version: 08.07.17



EAGLE BRIDGES PRODUCT DATA

PRODUCT: RHINO GUARD SUPER LINER

PRODUCT NUMBER: 3656

DESCRIPTION: Rhino Guard Super Liner is a specially engineered Epoxy based coating designed to provide exceptional protection for metals that are exposed to harsh chemicals and moist, wet conditions such as found in waste containers. **Rhino Guard Super Liner** is tough, flexible and adherent with a good thick film build for added durability.

PROPERTIES

VISCOSITY: 100 – 125 KU'S

POUNDS PER GALLON: 9.95 +/- .2

GLOSS: 5 – 10 (60 DEGREE GLOSS)

FLASH POINT: 80 DEG. F.

VOLATILE ORGANIC COMPOUND (VOC 2.0)

SOLIDS: by volume (+/-) 2% - 70%
by weight (+/-) 2% - 80%

THEORETICAL COVERAGE @ 1 mil dry: 1120 sq. ft. per gallon. No loss assumed.

FLEXABILITY: FIRM TACK RESISTANT FILM
IMPACT RESISTANCE: GOOD
ADHESION: EXCELLENT
HEAT RESISTANCE : DRY 250°F. WET 180°F.
HUMIDITY RESISTANCE: EXCELLENT
WATER IMMERSION: EXCELLENT
SALT SPRAY RESISTANCE: EXCELLENT

APPLICATION

PREPARATION: Apply to properly cleaned or treated surface. This may consist of solvent wiping, wire brushing, sandblasting, phosphate treatment or chemical etching.

TYPE OF APPLICATION: AIRLESS SPRAY OR PRESSURE POT.

REDUCTION: NONE
REDUCING SOLVENT: N/A

REDUCED VISCOSITY; N/A

RECOMMENDED DRY FILM: 6-10 mils DFT
RECOMMENDED PRIMER: NONE

CLEAN-UP SOLVENT: XYLOL OR NAPHTHA

DRY TIME: TACK FREE - 2 HOURS
RECOAT - 12 HOURS
FULL CURE - 7 – 10 DAYS

This information is offered in good faith as typical values and not as product specifications. No warranty, either expressed or implied, is made. The recommendations are believed to be generally applicable. However, each user should review these recommendations in the specific context of the intended use.

EAGLE BRIDGES MARATHON

Custom Engineered Industrial Paints, Coatings and Adhesions

P.O. Box 496 Byron, Georgia 31008, 478-956-5605 Fax: 478-956-3617



EAGLE BRIDGES PRODUCT DATA

PRODUCT: RHINO GUARD UL WR BLACK

Product Number: 200271901

DESCRIPTION: RHINO GUARD UL WR BLACK IS A LOW COST PROTECTIVE UNDER CARRIAGE COATING DESIGNED FOR USE ON OVER THE ROAD EQUIPMENT SUCH AS TRUCKS, TRAILERS, AUTOMOBILES, ETC. AS A RUST PREVENTATIVE. APPLIES IN A THICK FILM FOR MAXIMUM EFFICIENCY.

PROPERTIES	APPLICATION
<p>VISCOSITY: THIXOTROPIC HEAVY BODY</p> <p>POUNDS PER GALLON: 9.5 +/- .2</p> <p>GLOSS: DULL SATIN FINISH</p> <p>FLASH POINT: N/A</p> <p>VOLATILE ORGANIC COMPOUND (VOC) NONE</p> <p>SOLIDS: by volume (+/-) 2% - 47.9</p> <p style="padding-left: 40px;">by weight (+/-) 2% - 55.5</p> <p>THEORETICAL COVERAGE @ 1 mil dry: 768 sq. ft. per gallon. No loss assumed.</p> <p>FLEXABILITY: SOFT PLIABLE FILM IMPACT RESISTANCE.</p> <p>ADHESION: EXCELLENT</p> <p>HEAT RESISTANCE : SOFTENS</p> <p>HUMIDITY RESISTANCE: EXCELLENT</p> <p>WATER IMMERSION: EXCELLENT</p> <p>SALT SPRAY RESISTANCE: EXCELLENT</p>	<p>PREPARATION: Apply to properly cleaned or treated surface. This may consist of solvent wiping, wire brushing, sandblasting, phosphate treatment or chemical etching</p> <p>TYPE OF APPLICATION:</p> <p>Spray</p> <p>REDUCTION: NONE</p> <p>REDUCING SOLVENT: NONE</p> <p>REDUCED VISCOSITY ; N/A</p> <p>RECOMMENDED DRY FILM: 6-10 mils</p> <p>RECOMMENDED PRIMER: NONE</p> <p>CLEAN-UP SOLVENT: WATER</p> <p>DRY TIME : 30 MINUTES DEPENDING ON HUMIDITY AND TEMPERATURE.</p>

This information is offered in good faith as typical values and not as product specifications. No warranty, either expressed or implied, is made. The recommendations are believed to be generally applicable. However, each user should review these recommendations in the specific context of the intended use.

Custom Engineered Industrial Paints, Coatings and Adhesions
P.O. Box 496 Byron, Georgia 31008, 478-956-5605 Fax: 478-956-3617