

Eagle Bridges Company

216 Hwy 49 S.
Byron, GA 31008
800-541-1747
Eaglebridges.com



Product: Container Guard Satin Black Product Code: 4360

Description

This product is an air-drying, water reducible that is formulated to have excellent resistance to atmospheric corrosion and can be top coated with a variety of coatings.

Physical Properties

Property Description	Attribute	Property Description	Attributes
Viscosity	95-100 KU Stormer (+/-) 2	Weight Per Gallon	9.08 +/- .25
Gloss	5-25%	Specific Gravity	1.0904
Flash Point	n/a	Theoretical Coverage @1 mil dry: No loss assumed.	452 sq. ft. per gallon
Solids by Volume	28 (+/-) 2%	Solids by Weight	36 (+/-) 2%
Volatile Organic Content (V.O.C.) less exempt	2.74 # Per Gallon	Volatile Organic Content (V.O.C.) less exempt	328 Grams Per Liter
Hazardous Air Pollutants (H.A.P.s.)	0.1 #/gallon	Dry Time to Touch (@ 77 degrees F, 50% RH)	15-30 minutes
Dry Time to Handle (@ 77 degrees F, 50% RH)	30-60 minutes	Dry Time to Recoat (@ 77 degrees F, 50% RH)	4-16 hours

Dry Times

When multiple coats are applied, the dry time between coats depends upon film thickness, temperature and humidity. If the first coat is in the critical cure stage it may be lifted or blistered by the second coat. To test, apply a small swatch over first coat and observe for a few minutes. If no film distortion occurs, it is safe to recoat. When in doubt, allow one week before recoating.

Application

- **Preparation:** - Apply to properly cleaned or treated surface. This may consist of solvent wiping, wire brushing, sandblasting, phosphate treatment or chemical etching. All surfaces must be free of dust, oils and other surface contaminants before application.
- **Reduction:** as needed, water (use sparingly)
- **Method:** Spray, airless or Electrostatic if controlled, or brush or roll. Application properties can be adjusted with special solvents
- **Recommended Dry Film:** 1.0-2.0 mils
- **Primer:** 3455
- **Temperature:** Ambient temperature above 50 deg. F

Clean Up

Recommended solvent for clean-up is Water when wet or Xylene when dry

Safety and Other Information

For Safety and Handling information please consult the Safety Data Sheet (SDS)

For any other Information Please Contact Eagle Bridges Company, Inc.

800-541-1747 Phone

478-956-3617 Fax

Eaglebridges.com Website

This information is offered in good faith as typical values and not as product specifications. No warranty, either expressed or implied, is made. The recommendations are believed to be generally applicable. However, each user should review these recommendations in the specific context of the intended use.